

# BONDERITE C-NE N

July 2022

## PRODUCT DESCRIPTION

BONDERITE C-NE N provides the following product characteristics:

<b>Technology</b>	Industrial Cleaner
<b>Product Type</b>	Neutral Deruster
<b>Application</b>	Parts Cleaning, Derusting
Concentration in spray processes	20 to 30 g/l
Concentration in immersion process	30 to 100 g/l
Operating Temperature	20 to 70 °C

BONDERITE C-NE N is a neutral rust and scale remover designed for immersion and spray processes on a wide variety of materials including ferrous and non-ferrous metals. It is especially applicable for the removing of residues resulting from deburring processes or laser cutting.

## TECHNICAL DATA


Appearance	bright yellowish liquid
Density at 20°C, DIN 51757	~1.3 g/cm <sup>3</sup>
pH-value (depending on conc.)	5 to 7

### Bath Control:

Normally the BONDERITE C-NE N -bath is controlled by measuring conductivity and iron content. The iron content can be measured via AAS resp. ICP or for a first orientation via photometric measurement or test strips. The max. iron content should be 50 g/l but this limit can vary depending from application.

### Data for a fresh bath:

Conductivity of BONDERITE C-NE N



Temperature coefficient: 2.22 %/°C

## DIRECTIONS FOR USE

### Preliminary Statement:

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

### Standard Procedure:

The bath make-up is depending on the degree of rust or scale on the surface. Non-ferrous metals and other surfaces should be tested prior to use.

Add the required amount carefully to the circulation system.

Make-up for spray processes	2 to 3%
Make-up for immersion processes	3 to 10%
Temperature	20 to 70°C
Duration of treatment	depending on grade of rust

- Derusting with BONDERITE C-NE N
- Rinse (mechanically supported)
- Passivation
- Drying

### General Recommendation:

If BONDERITE C-NE N is used in front of a degreasing stage an addition of a surfactant package (0.2 to 0.5%) is recommended to improve wettability.

The life time of the bath is depending on the concentration and the iron content.

In special cases as an option for measurement of concentration following titration can be used after consulting our customer service (if a fresh bath is controlled the addition of triethanolamine is obsolete).

### Bath Control (Determination of active BONDERITE C-NE N in used bathes by titration):

- Pipette 10 mL of bath solution into an Erlenmeyer flask and dilute with 300 mL of distilled water.
- Add 1 to 2 indicator buffer tablets and stir until the indicator is solved.
- Add 2 mL triethanolamine to "mask" the solved iron.
- Add approx. 3 to 4 drops ammonia solution 25% and control the colour of the solution.
- If the colour changes to red directly, no active BONDERITE C-NE N is present in the bath
- If the color is strongly green titrate the sample with 0.1 N CaCl<sub>2</sub> solution until the colour changes from green to "dirty" red.
- The used mL 0,1 N CaCl<sub>2</sub> solution multiplied by 0.35 gives the content of active BONDERITE C-NE N in %.

**Materials:**

- Erlenmeyer flask, 300 ml
- Burette, 25 ml
- Indicator buffer tablets (Merck no. 1.08430.0500)
- Ammonia solution 25% (Merck no. 1.05432.1011)
- $\text{CaCl}_2 \times 2 \text{H}_2\text{O}$  (Merck 1.02382.0500)
- Deionized water
- Triethanolamine 99%
- Manufacturing of 0.1 N  $\text{CaCl}_2$  solution:  
weight 14.702 g  $\text{CaCl}_2 \times 2 \text{H}_2\text{O}$  into a 1000 ml volumetric flask and add deionized water until the mark is reached

**Classification:**

Please refer to the corresponding **Material Safety Data**

**Sheets** for details on:

**Hazards identification**

**Transport information**

**Regulatory information**

**Storage:**

Recommended Storage Temperature	0 to 40°C
Shelf-life, months	24 months
Frost-Sensitive	yes

**ADDITIONAL INFORMATION****Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2